CITADIN™ 60 SLAB
REGULAR OR SMOOTH PREMIUM ❶ FINISHES



A

CITADIN™ 60 SLAB - 400 x 600

	HEIGHT/WIDTH/LENGTH DIMENSIONS (CM)	DIMENSIONS (IN)	
	6 x 40 x 60	$2^{3/8}$ x $15^{3/4}$ x $23^{5/8}$	
Unit/Surface	4,17 / m²	0,39 / ft²	
Qty/row	0,96 m²	10,33 ft²	
Qty/cube	10,56 m²	113,63 ft²	11 rows
Weight/unit	37 kg	81 lb	
Weight/cube	1591 kg	3508 lb	

Specifications	Codes	Standard Colours
Regular finish	PTR-446R-15	Grey and charcoal
		Deluxe Colours
	PTR-446R-02	Ice grey
	PTR-446R-24	Travertine beige
Premium ❶ Finish	PTR-446L-21	Ivory beige

Approximate coverage areas for one bag of polymeric sand (22,7 kg) 17,65 m² 190,0 ft²



B

CITADIN™ 60 SLAB - 600 x 600

	HEIGHT/WIDTH/LENGTH DIMENSIONS (CM)	DIMENSIONS (IN)	
	6 x 60 x 60	$2^{3/8}$ x $23^{5/8}$ x $23^{5/8}$	
Unit/Surface	2,78 / m²	0,26 / ft²	
Qty/row	0,72 m²	7,75 ft²	
Qty/cube	7,92 m²	85,25 ft²	11 rows
Weight/unit	56 kg	123 lb	
Weight/cube	1200 kg	2646 lb	

Specifications	Codes	Standard Colours
Regular finish	PTR-466R-15	Grey and charcoal
		Deluxe Colours
	PTR-466R-02	Ice grey
	PTR-466R-24	Travertine beige
Premium ❶ Finish	PTR-466L-21	Ivory beige

Approximate coverage areas for one bag of polymeric sand (22,7 kg) 22,06 m² 237,5 ft²

COLOURS

REGULAR FINISH



● Grey and charcoal



● Ice grey



● Travertine beige


SMOOTH FINISH ❶




● Ivory beige

Colours with solar reflectance indices contributing to the LEED program in order to reduce the creationt of heat islands in urban areas as much as possible.


PATTERNS



Pattern 1
Checker pattern
(60 x 600 x 600)



Pattern 2
Runner pattern
(60 x 400 x 600)



Pattern 3
Runner pattern
(60 x 600 x 600)

The layout shown in the above illustration is for information purposes only. Bolduc disclaims all responsibility for the excess or lack of slabs resulting from an installation according to these laying patterns.

CITADIN™ 60 SLAB
REGULAR OR SMOOTH PREMIUM ❶ FINISHES

TECHNICAL INFORMATIONS

Product	Standard	Flexural (transverse) strength	Resistance to freeze-thaw cycles in a saline solution	Water absorption	Dimensional tolerances
Citadin 60 slab	CSA A231.1	5 MPa (725 psi)	Maximum loss of initial weight in a saline solution (NaCl 3 %) : 225 g/m² (0,74 oz / ft²) after 28 cycles 500 g/m² (1,64 oz / ft²) after 49 cycles	6 % maximum	Length: -1 mm to +2 mm (-1/32 in to + 5/64 in) Width: -1 mm to +2 mm (-1/32 in to + 5/64 in) Height: ±3 mm (±1/8 in)

When placing joint filler sand, we recommend using a Teflon-coated vibrating plate on pavers or slabs to protect stone surfaces.
Cover snow removal tools with Teflon or neoprene protectors to minimize the risk of damage from scratches.

CANADA : 1 800 463-8966
USA : 1 800 603-5567
WWW.BOLDUC.CA