

# LOTUS™ STONE

## PATINART FINISH



### LOTUS™ STONE

	HEIGHT/WIDTH/LENGTH	
	DIMENSIONS (CM)	DIMENSIONS (IN)
	5 x 30-38 x 43-63	2 x 12-15 x 17-25
Units/Surface	9,36 / m <sup>2</sup>	0,87 / ft <sup>2</sup>
Surface/unit	0,11 m <sup>2</sup>	1,15 ft <sup>2</sup>
Surface/cube	6,41 m <sup>2</sup>	69 ft <sup>2</sup>
Qty/cube	60	10 rows
Weight/unit avg.	12,5 kg	27,6 lb
Weight/cube	782 kg	1724 lb

SPECIFICATIONS	CODES	COLORS
	PTR-100P-15	Gray and charcoal
	PTR-100P-24	Travertine beige

6 different shapes for a more natural look.

Blend well with Sutton wallstone and Appalachian Stones.

Approximate coverage areas for one bag of polymeric sand ( 22,7 kg ) 10,52 m<sup>2</sup>    113,2 ft<sup>2</sup>

### COLORS




● Gray and charcoal



● Travertine beige

### PATTERN



Random pattern

The layout shown in the above illustration is for information purposes only. Bolduc disclaims all responsibility for the excess or lack of stones resulting from an installation according to these laying patterns.

### TECHNICAL INFORMATIONS

Product	Standard	Flexural (transverse) strength	Resistance to freeze-thaw cycles in a saline solution	Water absorption	Dimensional tolerances
Lotus stone	CSA A2311	5 MPa (725 psi)	Maximum loss of initial weight in a saline solution (NaCl 3 %): • 225 g/m <sup>2</sup> (0,74 oz / ft <sup>2</sup> ) after 28 cycles • 500 g/m <sup>2</sup> (1,64 oz / ft <sup>2</sup> ) after 49 cycles	6 % maximum	Length: -1 mm to +2 mm (-1/32 in to + 5/64 in) Width: -1 mm to +2 mm (-1/32 in to + 5/64 in) Height: ±3 mm (±1/8 in)